

TABLA No. 12B

PROPORCIONAMIENTO Y PROPIEDADES DEL CONCRETO ENDURECIDO
MEDICIONES DEL FLUJO PLASTICO.

SERIE	REVOLTURA No.	MEDICIONES DEL FLUJO PLASTICO **					
		f'c a los 28 DIAS kg/cm ²	f'c a los 28 DIAS kg/cm ²	ESFUERZO RELACION APLICADO ESFUERZO RESIST. kg/cm ²	DEF. UNIT. TOT. POR FLUJO PLAST.A 28 DIAS		
B-1	17	350	381	155	0.44	770 X 10 ⁻⁶	
	18	461	518	200	0.43	820 X 10 ⁻⁶	

* De la referencia (1)

** Todas las mediciones son sobre cilindros de 150 X 300 mm

REFERENCIAS

1. Ghosh, R.S. and Malhotra, V.M. "Use of superplasticizers as water reducers"; CANMET, Department of Energy, Mines and Resources, Ottawa, Canada; Report No. MRP/MSL 78-189 (J), 24 pp; October 1978.
2. Holbek, K. and Skrastins, J.I. "Canadian experience with the use of superplasticizers in the precast concrete industry"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada, 1978; Vol. 1, pp 183-200.
3. Hyland, E.J. "Use of Melment in precast pipe and tunnel sections"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada, 1978; Vol. 1, pp 201-214.
4. Johnson, C.D., Gamble, B.R. and Malhotra, V.M. "Superplasticizers: effects on properties of fresh and hardened concrete"; Paper to be presented at the 1979 TRB annual meeting, Washington, D.C., U.S.A.
5. Lane, R.O. and Best, J.F. "Laboratory studies on the effects of superplasticizers on the engineering properties of plain and fly ash concretes"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada, 1978; Vol. 1, pp 379-403.
6. Mailvaganam, N.P. "Slump loss in flowing concrete"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada, 1978, Vol. 2, 649-672.
7. Malhotra, V.M. and Malanka, D. "Performance of superplasticizers in concrete: laboratory investigation - Part 1"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada, 1978, Vol. 2, pp 673-708.
8. Malhotra, V.M. "Effect of repeated dosages of superplasticizers on workability, strength and durability of concrete"; CANMET, Department of Energy, Mines and Resources, Ottawa, Canada; Report No. MRP/MSL 78-40 (OP&J), 34 pp; February 1978.
9. Malhotra, V.M. "Performance of superplasticizers in high water to cement ratio concretes"; CANMET, Department of Energy, Mines and Resources, Ottawa, Canada; Report No. MRP/MSL 78-147 (OP&J), 34 pp; July 1978.
10. Malhotra, V.M. "Mechanical properties and freeze-durability of blast furnace slag/portland cement concretes"; Department of Energy, Mines and Resources, Ottawa, Canada; MRP/MSL Report under preparation.

11. Mather, B. "Tests of high-range water-reducing admixtures"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada; Vol. 1, pp 325-346.
12. Miclenz, R.C. and Sprouse, J.H. "High range water reducing admixtures: effect on the air-void system in air entrained and non-air-entrained concrete"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada; Vol. 1, pp 347-378; 1978.
13. Mukherjee, P.K. and Chojnacki, B. "Laboratory evaluation of a concrete superplasticizing admixture"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada; Vol. 1, pp 403-424; 1978.
14. Pistilli, M.F. and Bobrowski, G.S. "Relationship of concrete slump loss and cement chemistry in the presence of admixtures"; Paper to be presented at the 1979 TRB annual meeting in Washington, D.C.
15. Ramakrishnan, V. "Workability and strength of superplasticized concrete"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada; Vol. 2, pp 481-514; 1978.
16. Seabrook, P.T. and Malhotra, V.M. "Accelerated strength testing of superplasticized concrete and the effect of repeated doses of superplasticizers on properties of concrete"; Proceedings, International Symposium on Superplasticizers in Concrete, Ottawa, Canada; Vol. 2, pp 609-648; 1978.
17. Quon, D. and Malhotra, V.M. "Performance of superplasticizers in high alumina cement concrete"; Department of Energy, Mines and Resources, Ottawa, Canada; MRP/MSL Report under preparation.

EFFECTO DEL CONTENIDO DE SULFATO EN EL CEMENTO, SOBRE LA PERDIDA DE REVENIMIENTO EN CONCRETOS QUE CONTIENEN REDUCTORES DE AGUA DE GRAN EFICIENCIA (SUPERPLASTIFICANTES)

S. M. Kalil* y M. A. Ward **

PESUMEN

A temperaturas normales (22°C), los concretos que contienen superplasticificantes pierden mucha de su gran manejabilidad inicial en un lapso aproximado de cuarenta y cinco minutos desde el mezclado inicial. Cuando el concreto está caliente (40°C) este efecto se acelera al grado que la pérdida de manejabilidad (revenimiento) ocurre en treinta minutos.

Ya antes, los autores han demostrado que con aditivos reductores de agua convencionales (a base de ligno-sulfonato de calcio) los grados de la hidratación inicial del cemento pueden ser modificados alterando el contenido de SO_3 del cemento con el resultado de que las resistencias a largo plazo son aumentadas y el flujo plástico y la contracción son disminuidas.

En este trabajo se emplea un calorímetro de conducción para establecer el rango óptimo de contenido de SO_3 del cemento tipo I usado en el estudio, para pastas de cemento con y sin adición de superplasticificante y a dos temperaturas, 25°C y 40°C . Los concretos fueron elaborados a ambas temperaturas usando cementos con contenido de SO_3 tal como se determinó en el estudio del calorímetro.

Se concluye que existe un rango óptimo de contenido de SO_3 para el cual, la pérdida de manejabilidad (revenimiento) es minimizada en concretos que contienen superplasticificantes tanto a temperatura normal como a temperatura elevada. Por ejemplo, a 40°C , la manejabilidad no es relativamente afectada sino hasta 60 minutos después del mezclado, en mezclas tratadas y no tratadas, mientras que con contenido de SO_3 tal como se recibió, los concretos empezaron a perder manejabilidad en un grado significativo después de 30 minutos. También es de interés que se mejore la resistencia a la compresión a corto y largo plazo (nominalmente 12%) con el contenido óptimo de sulfato.

* Investigadora asociada en el Depto. de Ing. Civil de la Universidad de ---
Calgary, Calgary, Canadá.

** Profesor y Jefe del Depto. de Ing. Civil de la Universidad de Calgary.

Parece que alguna consideración debería ser dada para alterar el contenido de SO₃ de los cementos en clima caliente, particularmente cuando los superplasticantes son usados en la revolitura, procurando que la resistencia y la durabilidad del concreto sean adecuadas.

EFFECTO DEL CONTENIDO DE SULFATO EN EL CEMENTO, SOBRE LA PERDIDA DE REVENIMIENTO EN CONCRETOS QUE CONTIENEN REDUCCIONES DE AGUA DE GRAN EFICIENCIA (SUPERPLASTIFICANTES).

I N D I C E

	Pág.
RESUMEN.	165
INTRODUCCION.	169
PROCEDIMIENTO EXPERIMENTAL	170
RESULTADOS Y DISCUSIONES	171
CONCLUSIONES.	176
RECONOCIMIENTOS	177
REFERENCIAS	194